

~~RESTRICTED~~**NACA**

0069276

TECH LIBRARY KAFB, NM

RESEARCH MEMORANDUM

PRELIMINARY INVESTIGATION OF EFFECTS OF ALPHA-PARTICLE
BOMBARDMENT ON THE CREEP RATE OF ALUMINUM

By J. Howard Kittel

REVISION
COPIES

Flight Propulsion Research Laboratory
Cleveland, Ohio

AFMDC
TECHNICAL
AFL 2011

CLASSIFIED DOCUMENT

This document contains classified information affecting the National Defense of the United States within the meaning of the Espionage Act, USC 793 and 794. Its transmission or the revelation of its contents in any manner to an unauthorized person is prohibited by law. Information so classified may be imparted only to persons in the military and Naval Services of the United States, appropriate civilian officers and employees of the Federal Government who have a legitimate interest therein, and to United States citizens of known loyalty and discretion who of necessity must be informed thereof.

TECHNICAL
EDITING
WAIVED

NATIONAL ADVISORY COMMITTEE FOR AERONAUTICS

WASHINGTON

July 3, 1947

Declassified by Authority of
LARC Security Classification
office (SCO) letter dated June 16, 1983

Maurice F. Sommer

~~RESTRICTED~~

319.98/13

1947

E 7 E 13

6544

FILE
National Aeronautics and
Space Administration
Langley Research Center
Hampton, Virginia
23665

NASA

Reply to AIN of

139A

JUN 1 6 1983

TO: Distribution

FROM: 180A/Security Classification Officer

SUBJECT: Authority to Declassify NACA/NASA Documents Dated Prior to
January 1, 1960

(informal correspondence)
Effective this date, all material classified by this Center prior to
January 1, 1960, is declassified. This action does not include material
derivatively classified at the Center upon instructions from other Agencies.

Immediate re-marking is not required; however, until material is re-marked by
lining through the classification and annotating with the following statement,
it must continue to be protected as if classified:

"Declassified by authority of LARC Security Classification Officer (SCO)
letter dated June 16, 1983," and the signature of person performing the
re-marking.

If re-marking a large amount of material is desirable, but unduly burdensome,
custodians may follow the instructions contained in NWS 1640.4, subpart F,
section 1203.604, paragraph (h).

This declassification action complements earlier actions by the National
Archives and Records Service (NARS) and by the NASA Security Classification
Officer (SCO). In Declassification Review Program 807008, NARS declassified
the Center's "Research Authorization" files, which contain reports, Research
Authorizations, correspondence, photographs, and other documentation.
Earlier, in a 1971 letter, the NASA SCO declassified all NACA/NASA formal
series documents with the exception of the following reports, which must
remain classified:

Document No.

E-51A30
E-53G20
E-53G21
E-53K18
SL-54J21a
E-55C16
E-56H23a

First Author

Nagey
Francisco
Johnson
Spoonier
Westphal
Fox
Himmel

JUN 2 1 1983

If you have any questions concerning this matter, please call Mr. William L. Simkins at extension 3281.

Jess G. Ross
 Jess G. Ross
 2898

Distribution:
 SDL 031

CC:
 NASA Scientific and Technical
 Information Facility
 P.O. Box 8757
 BWI Airport, MD 21240

NASA--NIS-5/Security
 180A/RIAD
 139A/TU4AO

139A/WLSimkins:elf 06/15/83 (3281)

139A/JS 6-15-83

31-01 HEADS OF ORGANIZATIONS
 HESS, JANE S.
 MAIL STOP 188
 BLOC 1194



0069276

NACA RM No. E7EL3

~~RESTRICTED~~

NATIONAL ADVISORY COMMITTEE FOR AERONAUTICS

RESEARCH MEMORANDUMPRELIMINARY INVESTIGATION OF EFFECTS OF ALPHA-PARTICLE
BOMBARDMENT ON THE CREEP RATE OF ALUMINUM

By J. Howard Kittel

SUMMARY

A preliminary investigation was made to determine the effects of alpha-particle bombardment on the creep rate of aluminum wire at 400° F. The alpha radiation from an 85-millicurie polonium source appeared to decrease slightly the creep rate of the aluminum. A metallographic examination of the creep specimens showed no microstructural changes that could be attributed to the alpha-particle bombardment.

INTRODUCTION

The fundamental research at the NACA Cleveland laboratory on the physical properties of materials includes a study of the mechanism of creep. As a part of this study a preliminary investigation was made to determine the effect of alpha-particle bombardment on the creep rate of a commercially pure polycrystalline metal, aluminum. Although the penetration of these particles in metals is small, they possess high energies. There is a possibility that these energies might be sufficient to affect the process of creep in polycrystalline metals. Work by Andrade (reference 1) indicated that, in the case of single crystals of cadmium, alpha radiation can increase creep rates as much as five times. No reference describing creep of polycrystalline metals under alpha-particle bombardment has been found in the literature.

Results from the preliminary investigation described in this paper are presented in the form of curves showing total elongations obtained for each specimen as a function of time. Results are also presented from a metallographic study made on the creep specimens to detect any changes in the microstructure that might have resulted from the alpha-particle bombardment.

~~RESTRICTED~~

APPARATUS AND PROCEDURE

Commercially pure aluminum wire was used for the creep investigation because of its availability and because its low density would enable greater penetration of the bombarding particles. The diameter of the wire, measured with a filar micrometer, was 0.01014 ± 0.00002 inch. The alpha-particle source was 85 millicuries of polonium plated on a foil that was bent into a U-shape and placed at a radial distance of 2 millimeters from the specimen. Radioactive decay of the polonium decreased its activity to 80 millicuries during the time required for the experiments. The length of the foil was 25 millimeters, which was sufficient to irradiate uniformly the 20-millimeter gage length of the specimen. Previous work showed that the presence of a foil about the specimen slightly decreased its creep rate. This effect probably resulted from a slight difference in temperature of the specimen caused by prevention of heat absorption by the foil from the walls of the furnace. In order to remove the effect of this variable, the nonirradiated creep specimens were surrounded with a foil of dimensions and reflectivity similar to those of the radioactive foil.

In order to remove the effects of any previous cold-working, all specimens were simultaneously annealed at 675° F for 15 minutes before being stressed. The creep determinations were made at an ambient-air temperature of $400^{\circ} \pm 2^{\circ}$ F measured by a thermocouple immediately adjacent to the specimen. According to reference 2 (p. 200), this temperature is about 100° F above the recrystallization temperature of aluminum. In order to obtain a uniform specimen temperature, and to maintain complete accessibility of the specimen during testing, a furnace with a circulating atmosphere was used (fig. 1). The variation in ambient temperature along the gage length of the specimen was less than $\pm 1.5^{\circ}$ F. Measurements of the distance between gage marks on the specimen were made through a glass window in the furnace by means of a telescope mounted on a micrometer slide that could be read to 0.001 millimeter. The specimens were stressed to 2910 pounds per square inch by a directly suspended weight.

A metallographic study was made of specimens after the annealing operation, after being stressed under alpha radiation, and after being stressed without alpha radiation.

RESULTS AND DISCUSSION

The results of eight creep determinations, made in the order indicated by the test number, are shown in figure 2. Elongation

data are given for four specimens subjected to alpha-particle bombardment during testing and for four specimens that were not irradiated. It can be noted that the elongations of specimens not subjected to radiation tend to be somewhat greater than those of specimens that were irradiated, although much overlapping of the data is apparent, particularly at the longer periods of time.

Second-stage (approximately constant-rate) creep predominated in the tests during the interval between 20 and 90 minutes test time. After 90 minutes, third-stage (increasing-rate) creep and rupture of the specimens occurred. No creep determinations were made beyond 180 minutes. The creep rates of the eight specimens during the period of second-stage creep are given in the following table.

| With alpha radiation | | Without alpha radiation | |
|----------------------|---------------------------------|-------------------------|---------------------------------|
| Test | Creep rate (percent/ min) | Test | Creep rate (percent/ min) |
| 1 | 0.065 | 2 | 0.085 |
| 4 | .070 | 3 | .073 |
| 7 | .083 | 5 | .075 |
| 8 | .064 | 6 | .076 |
| Average | .071 | Average | .077 |

The average second-stage creep rate of the four specimens subjected to alpha-particle bombardment was 0.071 percent per minute; whereas the average second-stage creep rate of the four nonirradiated specimens was 0.077 percent per minute or about 8 percent greater. On the basis of results obtained in this preliminary investigation, it appears that alpha-particle bombardment might have very slightly decreased the creep rate of the aluminum wire. Great significance, however, should not be given to these results because of the limited number of experiments.

As was previously mentioned, determinations of the effect of alpha radiation on the creep rate of single crystals of cadmium have shown an accelerating effect (reference 1). It appears therefore that the effects of alpha-particle bombardment on creep rates of materials may depend upon the nature of the material and upon the number of crystals in the test section.

The metallographic examinations of the specimens showed no changes in the microstructure that could be attributed to the alpha radiation.

SUMMARY OF RESULTS

The following results were noted in determinations of the creep rates of aluminum wire with and without alpha-particle bombardment:

1. Alpha-particle bombardment from an 85-millicurie polonium source appeared to decrease slightly the creep rate of polycrystalline aluminum wire at 400° F.

2. No metallographic changes were noted in the aluminum specimens that could be attributed to the alpha-particle bombardment.

Flight Propulsion Research Laboratory,
National Advisory Committee for Aeronautics,
Cleveland, Ohio

REFERENCES

1. Andrade, E. N. da C.: Effect of Alpha-Ray Bombardment on Glide in Metal Single Crystals. *Nature*, vol. 156, no. 3952, July 28, 1945, pp. 113-114.
 2. Archer, R. S.: Heat Treatment of Metals. *Metals Handbook*, Am. Soc. Metals (Cleveland), 1939 ed., pp. 198-206.
-




Figure 1. - Furnace used for creep-rate observations on aluminum wire at 400° F. The furnace utilizes an atmosphere moving in a closed circuit to obtain uniform specimen temperature and maximum accessibility of the specimen.




Figure 2. - Creep curves for eight aluminum specimens stressed at 2010 pounds per square inch at 400° F.